

AMENDMENTS TO THE CLAIMS:

Claims 21-26 are canceled without prejudice or disclaimer. Claims 8, 9, 10, 13, 14, 15, 18, 19 and 20 are amended. The following is the status of the claims of the above-captioned application, as amended.

1. (Original.) A method for preparing a particulate composition having improved average strength of particles comprising contacting a particulate starting material with a liquid and subjecting the mixture to high shear at a rate substantially avoiding agglomeration of particles.
2. (Original.) The method of claim 1 further comprising the step of isolating a fraction of particles comprising, containing or consisting of unbroken or whole particles from the particulate starting material having a higher average particle strength than the particles of the particulate starting material.
3. (Original.) The method of claim 2 comprising:
 - (a) providing a particulate starting material to be improved
 - (b) providing a liquid
 - (c) subjecting the particulate starting material and liquid to high shear treatment wherein the amount of liquid added and the high shear rate is adjusted as to substantially avoid agglomeration of particles and
 - (d) separating a desired fraction of particles wherein the desired fraction of particles obtained by separation has a higher average particle strength compared to the same fraction obtained from the starting particulate material provided in (a).
4. (Original.) The method according to claim 1, wherein the particulate starting material is characterised by having a particle size of at least 50 μm .
5. (Original.) The method according to claim 1, wherein the particulate starting material is characterised by having a particle size of at least 100 μm .
6. (Original.) The method according to claim 1, wherein the particulate starting material is characterised by having a particle size of at least 200 μm .
7. (Original.) The method according to claim 1, wherein the particulate starting material is characterised by having a particle size of less than 800 μm .

8. (Currently Amended.) The method according to ~~any of the claims 1 to 7~~claim 1, wherein said particulate starting material has a density of at least 1.3 g/cm³.
9. (Currently Amended.) The method according to ~~any of the claims 1 to 7~~claim 1, wherein said particulate starting material has a density of at least 1.5 g/cm³.
10. (Currently Amended.) The method according to ~~any of the claims 1 to 9~~claim 1, wherein the particulate starting material is granules comprise an active compound.
11. (Original.) The method according to claim 10, wherein the active compound is an enzyme.
12. (Original.) The method according to claim 1, wherein the particulate material is selected from the group of salt and sugar.
13. (Currently Amended.) The method according to ~~any of the claims 1 to 12~~claim 1, wherein the liquid is water or oil.
14. (Currently Amended.) The method according to ~~any of the claims 1 to 12~~claim 1, wherein the liquid is aqueous.
15. (Currently Amended.) The method according to ~~any of the claims 1 to 12~~claim 1, wherein the liquid is a saturated solution of one or more of the compounds present in the particulate material.
16. (Original.) The method according to claim 13, wherein salt, carbohydrates, binders, fibres, fillers, or other conventional coating materials are added to the liquid.
17. (Original.) The method according to claim 1, wherein the particulate material is water soluble.
18. (Currently Amended.) The method according to ~~any of claims 1 to 17~~claim 1, wherein the high shear treatment performed in a high shear mixer and the applied shear is in the range of 0.5 and 3 s⁻¹.
19. (Currently Amended.) The method according to ~~any of the claims 1 to 18~~claim 1, further comprising the step of drying the high shear treated particulate material.

20. (Currently Amended.) The method according to ~~any of the claims 1 to 19~~claim 1, wherein the particulate material and liquid are exposed to high shear until at least 5 % of the particles are destroyed or ~~or~~ broken down to a size outside the size distribution of the particulate starting material.

Claim 21-26 (Cancelled.)